




## OKS 1112 - Product Information

### Fields of Application:

Lubrication of closing devices and taps, as well as ground joints in industrial vacuum and laboratory equipment, if the consistency of other OKS silicone greases is insufficient.

### OKS 1112 Silicone grease for vacuum taps



### Advantages and Benefits:

No carbonization, no melting, steam pressure stays negligible up to +200 °C. Nearly constant consistency between -30 and +200 °C. No corrosive influence on metals and no softening influence on rubber and plastics. Good resistance against solvents and excellent resistance against numerous chemical agents. Resistive to cold and hot water, acetone, ethanol, ethylenglycole, glycerine and methanol, most of diluted bases and acids mineral and vegetable oils and numerous organic compounds and almost all usual gases.

### Application:

For best results, clean lubricant points and surfaces carefully, e.g. with OKS 2610 or OKS 2611. Apply grease evenly thin to the function point (e.g. with a brush or spatula etc.). Avoid excess. Observe the instructions of the machine manufacturer. Only mix with appropriate lubricants. Silicone-based plastics, e.g. silicone rubber, can be dissolved by silicone grease. Silicone grease must not be applied to sliding surfaces under influence of pure oxygen. For further questions please contact our Technical department.

### Additional Information:

Packaging (Article number):

- 500 g Tin (01112031)
- 5 kg Hobbock (01112050)
- 25 kg Hobbock (01112062)

Version  
E-06.1/10

The data in this brochure are the result of extensive testing and experience and meet the latest stage of engineering. Due to the diversity of application possibilities and technical realities they can only be recommendations and are not arbitrarily transferable; thus no obligations, liability or warranty claims can be derived herefrom. We accept liability for the fitness of our products for particular purposes and accept such liability in writing in the individual case. In any event any justified warranty claims shall be limited to the delivery of replacement goods which are free from defect or, in the event that such subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular but without limitation any liability for consequent damage, shall be excluded. Prior to use own testing must be done to prove suitability. The data are subject to change for the sake of technical progress. ® = Registered Trademark



## OKS 1112 Silicone grease for vacuum taps

### Technical Data

	Norm	Conditions	Unit	Value
Classification	DIN 51 502	DIN 51 825		MSI3S-30
<b>Base Oil</b>				
Type				Polydimethylsiloxane
Viscosity	din 51 562-1	25 °C	mm <sup>2</sup> /s	100.000
Pourpoint	DIN ISO 3016	3°C step	°C	-40
<b>Thickener</b>				
Type				anorganic
Consistency	DIN 51 818	DIN ISO 2137	NLGI- class	3
Worked penetration	DIN ISO 2137	60 Dh	0,1 mm	220 - 250
Evaporation loss	DIN 58 397-1	24h/200 °C	Weight-%	< 3,0
Oil separation	DIN 51 817	18h/40°C	Weight-%	0,00
		168h/40°C	Weight-%	0,14
Oxidation resistance	DIN 51 808	100h/160°C	bar	< 0,7
<b>Application Data</b>				
Density	DIN EN ISO 3838	+20°C	g/ml	1,0
Colour				transparent
<b>Service Temperatures</b>				
Minimum service temperature			°C	-30
Maximum service temperature			°C	200

The data in this brochure are the result of extensive testing and experience and meet the latest stage of engineering. Due to the diversity of application possibilities and technical realities they can only be recommendations and are not arbitrarily transferable; thus no obligations, liability or warranty claims can be derived herefrom. We accept liability for the fitness of our products for particular purposes and accept such liability in writing in the individual case. In any event any justified warranty claims shall be limited to the delivery of replacement goods which are free from defect or, in the event that such subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular but without limitation any liability for consequent damage, shall be excluded. Prior to use own testing must be done to prove suitability. The data are subject to change for the sake of technical progress. ® = Registered Trademark