

**OKS 2771** 

PTFE, Spray

**High-Pressure** 

Lubrication Paste with

0

# OKS 2771 - Product Information

## **Fields of Application:**

Lubrication of sliding machine elements of metal, plastic and ceramic, e.g. for cold and hot-water fixtures, for lubricating and sealing off tap cocks, labyrinth seals, stuffing boxes and packings. For lubricating and sealing off drain fittings for commercial kitchens, as a lubricant for threaded spindles on radiator thermostats etc. For long-term lubrication of heavily loaded press and guide plates on telescope booms of mobile cranes.

### Advantages and Benefits:

Reduces friction and wear, protects against corrosion, prevents stick-slip effects. High resistance to oxidation and ageing, non-toxic. Does not drip or melt in specified temperature range. Extremely noise and vibration-damping. Excellent resistance to cold and hot water, water vapour, lactic, formic, acetic and fruit acid, as well as alkaline and acidic cleaning agents and disinfectants. Suitable for use in the food processing and beverage industry. Hygienically harmless as defined in Art. 21, Para. 1 of the Foodstuffs and Essential Commodities Act. Generally good compatibility with elastomers and plastics. Elastic rubber materials such as EPDM and NBR are not attacked. For other plastic parts, a resistance test should be conducted to be on the safe side.



#### Application:

For best adhesion, clean contamination and other lubricants from slide surfaces. Best way is to clean mechanically first and then with OKS 2610 or OKS 2611 universal cleaning agent. Spray evenly a suitable quantity of paste onto surface. The paste will also act as a sealant. Do not use paste instead of grease and mix only with suitable lubricants. Our customer advice service will be pleased to help should you have any further questions.

#### **Additional Information:**

Packaging (Article number): - 400 ml Spray (02771004)

Version: E-06.1/09

The data in this brochure are the result of extensive testing and experience and meet the latest stage of engineering. Due to the diversity of application possibilities and technical realities they can only be recommendations and are not arbitratily transferable; thus no obligations, liability or warranty claims can be derived herefrom. We accept liability for the fitness of our products for particular purposes and accept such liability in writing in the individual case. In any event any justified warranty claims shall be limited to the delivery of replacement goods which are free from defect or, in the event that such subsequent improvement fails, to reimburesement of the purchase price. Any and all further claims, in particular but without limitation any liability for consequent damage, shall be excluded. Prior to use own testing must be done to prove suitability. The data are subject to change for the sake of technical progress. ® = Registered Trademark



## **Technical Data**

	Norm	Conditions	Unit	Value
Base Oil				
Туре				Ester
Viskosity	DIN 51 562-1 DIN 51 562-1	40°C 100°C	mm²/s mm²/s	5.000 340
Thickener				
Туре				PTFE
Unworked penetration	DIN ISO 2137		0,1 mm	220 - 250
Drop point	DIN ISO 2176		°C	none
Application Data				
Density	DIN 51 575	+20°C	g/cm <sup>3</sup>	1,23
Colour				white
Service Temperatures				
Minimum service temperature			°C	-20
Maximum service temperature			°C	150
Wear Protection Tests				
VBT- weld load (Four ball test rig)	DIN 51 350-4		N	2.200

The data in this brochure are the result of extensive testing and experience and meet the latest stage of engineering. Due to the diversity of application possibilities and technical realities they can only be recommendations and are not arbitratily transferable; thus no obligations, liability or warranty claims can be derived herefrom. We accept liability for the fitness of our products for particular purposes and accept such liability in writing in the individual case. In any event any justified warranty claims shall be limited to the delivery of replacement goods which are free from defect or, in the event that such subsequent improvement fails, to reimburesement of the purchase price. Any and all further claims, in particular but without limitation any liability for consequent damage, shall be excluded. Prior to use own testing must be done to prove suitability. The data are subject to change for the sake of technical progress. (B) = Registered Trademark